



WA. ALLOY CO.

WASHINGTON ALLOY'S Quality Management System is Certified to **ISO 9001:2008**
Cert # 05-R0925

308L Welding Wire and Rod



American Welding Society
Sustaining Company Member



ALLOY DESCRIPTION AND APPLICATION;

308L is a austenitic stainless steel used to weld base metal of similar composition types such as AISI 201(17-4 Mn), 202(18-5 Mn), 205, 301(17-7), 302(18-8), 304(19-9), 305(18-10), 308(20-10) also the low carbon grades. The low carbon reduces carbide precipitation (Tri-mix gas = 90%He+7.5%Ar+2.5%CO₂)

TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stick-out	Tri-mix (cfh)
0.023	180-400	30-85	14-19	3/8-1/2"	20-25
0.030	150-350	45-125	15-20	3/8-1/2"	20-25
0.035	120-330	60-150	16-22	3/8-1/2"	20-30
0.045	100-280	90-210	17-22	3/8-1/2"	25-30
<i>Spray 0.030</i>	<i>280-600</i>	<i>160-220</i>	<i>24-28</i>	<i>3/8-1/2"</i>	⁽¹⁾ 25-35
<i>0.035</i>	<i>250-470</i>	<i>170-295</i>	<i>23-29</i>	<i>1/2-3/4"</i>	⁽¹⁾ 25-35
<i>0.045</i>	<i>200-385</i>	<i>195-360</i>	<i>24-30</i>	<i>1/2-3/4"</i>	⁽¹⁾ 30-35
<i>1/16"</i>	<i>110-200</i>	<i>210-380</i>	<i>25-31</i>	<i>1/2-3/4"</i>	⁽¹⁾ 35-40

⁽¹⁾ 98%Ar
2%O₂

TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	80-150	12	3/8"	20	1/16-1/8"
3/32"	3/32"	150-250	12	3/8"	20	1/8- 3/16"
1/8"	1/8"	200-375	12	1/2"	25	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL WIRE CHEMISTRY (%) & WELD METAL PROPERTIES

Carbon	0.01	Tensile Strength (psi)	86,500
Manganese	1.77	Yield Strength (psi)	59,000
Silicon	0.37	Elongation	35 %
Molybdenum	0.03		
Nickel	9.64	Phosphorus	0.021
Chromium	19.75	Sulfur	0.003
Copper	0.04	Nitrogen	0.019

AVAILABLE SIZES: TS 308L = Spools of 023, 030, 035, 045, 1/16, 5/64, 3/32, 1/8, 3/16
TT 308L = Cut lengths of 023, 030, 035, 045, 1/16, 5/64, 3/32, 1/8, 5/32, 3/16
Other sizes available – please inquire

SPECIFICATIONS; ANSI/AWS A5.9 ER308L
ASME SFA 5.9 ER308L



2012 DC

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.