



WASHINGTON ALLOY'S Quality  
Management System is  
Certified to ISO 9001:2008  
Cert # 05-R0925

# 316L Welding Wire and Rod



 **American Welding Society**  
Sustaining Company Member



### ALLOY DESCRIPTION AND APPLICATION;

316L is similar to USA 316 but contains an average .02%

carbon producing a weld deposit with excellent resistance against intergranular corrosion caused by carbide precipitation. USA 316L is used for welding AISI types 316L, 318, and 319L that may be exposed to organic and inorganic acids. (Tri-mix gas = 90%He+7.5%Ar+2.5%CO<sub>2</sub>)

### TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stick-out	Tri-mix (cfh)
0.023	180-400	30-85	14-19	3/8-1/2"	20-25
0.030	150-350	45-125	15-20	3/8-1/2"	20-25
0.035	120-330	60-150	16-22	3/8-1/2"	20-30
0.045	100-280	90-210	17-22	3/8-1/2"	25-30
<i>Spray 0.030</i>	<i>280-600</i>	<i>160-220</i>	<i>24-28</i>	<i>3/8-1/2"</i>	<sup>(1)</sup> 25-35
<i>0.035</i>	<i>250-470</i>	<i>170-295</i>	<i>23-29</i>	<i>1/2-3/4"</i>	<sup>(1)</sup> 25-35
<i>0.045</i>	<i>200-385</i>	<i>195-360</i>	<i>24-30</i>	<i>1/2-3/4"</i>	<sup>(1)</sup> 30-35
<i>1/16"</i>	<i>110-200</i>	<i>210-380</i>	<i>25-31</i>	<i>1/2-3/4"</i>	<sup>(1)</sup> 35-40

<sup>(1)</sup> 98%Ar  
2%O<sub>2</sub>

### TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	80-150	12	3/8"	20	1/16-1/8"
3/32"	3/32"	150-250	12	3/8"	20	1/8- 3/16"
1/8"	1/8"	200-375	12	1/2"	25	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

### TYPICAL WIRE CHEMISTRY RANGE (%) & WELD METAL PROPERTIES from AWS A5.4

Carbon	0.03 max.	Tensile Strength (psi)	70,000 min.
Manganese	1.0-2.5	Elongation	30 % min.
Silicon	0.30-0.65		
Molybdenum	2.0-3.0		
Nickel	11.0-14.0	Phosphorus	0.03 max.
Chromium	18.0-20.0	Sulfur	0.03 max.
Copper	0.75 max.		

**AVAILABLE SIZES:** TS 316L = Spools of 023, 030, 035, 045, 1/16, 3/32, 1/8, 3/16

TT 316L = Cut lengths of 023, 030, 035, 045, 1/16, 5/64, 3/32, 1/8, 5/32, 3/16

Other sizes available – please inquire

**SPECIFICATIONS;** ANSI/AWS A5.9 ER316L  
ASME SFA 5.9 ER316L



2012 DC

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.