



# CERTIFICATE of Compliance



Quality Management System  
in accordance with  
**ISO 9001:2000**  
Cert # 05-R0925

**TRADE NAME: USA 70S-6**  
Specification: AWS A 5.18 : ASME SFA 5.18  
Classification: ER70S-6

Arc-Zone.com

## Chemical Composition % for Weld Wire

	AWS Requirements	Typical <sup>1</sup>
<b>Carbon (C)</b>	<b>0.06-0.15</b>	<b>0.10</b>
<b>Manganese (Mn)</b>	<b>1.40-1.85</b>	<b>1.70</b>
<b>Silicon (Si)</b>	<b>0.80-1.15</b>	<b>1.00</b>
<b>Phosphorus (P)</b>	<b>0.025 max.</b>	<b>0.010</b>
<b>Sulfur (S)</b>	<b>0.035 max.</b>	<b>0.015</b>
<b>Nickel (Ni)</b>	<b>0.15 max.</b>	
<b>Molybdenum (Mo)</b>	<b>0.15 max.</b>	
<b>Copper (Cu)</b>	<b>0.50 max.</b>	
<b>Chromium (Cr)</b>	<b>0.15 max.</b>	
<b>Vanadium (V)</b>	<b>0.03 max.</b>	

## Mechanical Properties

	Minimum AWS Requirements	Typical <sup>1</sup>
<b>Tensile Strength</b>	<b>70,000 psi</b>	<b>90,000 psi</b>
<b>Yield Strength</b>	<b>58,000 psi</b>	<b>73,000 psi</b>
<b>Elongation in 2"</b>	<b>22 %</b>	<b>25%</b>
<b>Charpy V-notch Impact Average</b>	<b>20 ft · lbs at -20°F</b>	<b>28 ft · lbs at -20°F</b>

This certification is provided by Washington Alloy Co., a U.S. Alloy Co., with the expressed understanding that if the product supplied fails to conform to the stated specifications, there shall be no personal liability of any kind on the undersigned and the obligation and liability of Washington Alloy Co., with respect to such non-conformance or specification failure, shall be limited to

- 1) an obligation to furnish the purchaser, at no additional charge, material that meets the specifications and conformances or
- 2) to refund to the purchaser the full amount of money paid to Washington Alloy Co. for the return of the product in full.

In no event shall Washington Alloy be liable for consequential damage.

**This certifies that the product supplied will meet the requirements of the noted classification and data above. Products supplied in accordance to the Quality Management System of Washington Alloy Company.**

Certification Administrator

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.



**Arc-Zone.com, Inc.**

760-931-1500 – sales@arc-zone.com  
2091 Las Palmas Drive, Ste. F – Carlsbad, CA 92011-1551 - USA